

種類	強度等級				含水率			
	強度等級	本数	比率 (%)	強度等級分布図	含水率	本数	比率 (%)	含水率分布図
杉正角	E 50	435	3.6		15%以下	9,336	77.4	
	E 70	3,212	26.6		15~20%	1,854	15.4	
	E 90	5,355	44.4		20~25%	862	7.1	
	E 110	2,528	21.0		25%以上	9	0.1	
	E 130	484	4.0		合計	12,061	100.0	
	E 150	47	0.4					
	合計	12,061	100.0					
杉平角	E 50	11	1.8		15%以下	524	84.9	
	E 70	108	17.5		15~20%	70	11.3	
	E 90	272	44.1		20~25%	23	3.8	
	E 110	181	29.3		25%以上	0	0.0	
	E 130	44	7.1		合計	617	100.0	
	E 150	1	0.2					
	合計	617	100.0					
桧正角	E 50	18	0.1		15%以下	20,703	94.3	
	E 70	247	1.1		15~20%	1,231	5.6	
	E 90	2,737	12.5		20~25%	2	0.1	
	E 110	9,272	42.3		25%以上	0	0.0	
	E 130	7,714	35.1		合計	21,936	100.0	
	E 150	1,948	8.9					
	合計	21,936	100.0					