







種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50	181	3.1		15%以下	4,237	76.8	
	E70	1,272	22.0		15~20%	1,250	22.7	
	E90	2,555	44.2		20~25%	30	0.5	
	E110	1,483	25.6		25%以上	0	0.0	
	E130	262	4.6		合計	5,517	100.0	
	E150	30	0.5					
	合計	5,783	100.0					
杉平角	E50	31	2.9		15%以下	907	91.8	
	E70	264	24.6		15~20%	81	8.2	
	E90	527	49.1		20~25%	0	0.0	
	E110	212	19.8		25%以上	0	0.0	
	E130	39	3.6		合計	988	100.0	
	E150	0	0.0					
	合計	1,073	100.0					
桧正角	E50	14	0.1		15%以下	20,445	91.8	
	E70	189	0.8		15~20%	1,823	8.2	
	E90	2,769	12.1		20~25%	0	0.0	
	E110	10,149	44.3		25%以上	0	0.0	
	E130	7,956	34.7		合計	22,268	100.0	
	E150	1,834	8.0					
	合計	22,911	100.0					