







種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50	241	4.2		15%以下	4,302	77.1	
	E70	1,670	28.8		15~20%	1,258	22.6	
	E90	2,551	44.0		20~25%	19	0.3	
	E110	1,134	19.5		25%以上	0	0.0	
	E130	185	3.2		合計	5,579	100.0	
	E150	16	0.3					
	合計	5,797	100.0					
杉平角	E50				15%以下			
	E70				15~20%			
	E90				20~25%			
	E110				25%以上			
	E130				合計	0	0.0	
	E150							
	合計	0	0.0					
桧正角	E50	106	0.4		15%以下	27,866	95.0	
	E70	442	1.5		15~20%	1,442	5.0	
	E90	4,496	15.3		20~25%	0	0.0	
	E110	13,316	45.4		25%以上	0	0.0	
	E130	9,318	31.8		合計	29,308	100.0	
	E150	1,646	5.6					
	合計	29,324	100.0					