







種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50 (6.9以下)	1,635	15.8		15%以下	7,070	72.7	
	E70 (7.0~8.9)	4,686	45.1		15~20%	2,580	26.6	
	E90 (9.0~10.9)	3,303	31.8		20~25%	63	0.7	
	E110 (11.0~12.9)	691	6.7		25%以上	0	0.0	
	E130 (13.0~14.9)	57	0.6		合計	9,713	100.0	
	E150 (15.0以上)	0	0.0					
	合計	10,372	100.0					
杉平角	E50 (6.9以下)	223	11.9		15%以下	1,552	93.1	
	E70 (7.0~8.9)	816	43.3		15~20%	115	6.9	
	E90 (9.0~10.9)	689	36.6		20~25%	0	0.0	
	E110 (11.0~12.9)	138	7.3		25%以上	0	0.0	
	E130 (13.0~14.9)	14	0.8		合計	1,667	100.0	
	E150 (15.0以上)	1	0.1					
	合計	1,881	100.0					
桧正角	E50 (6.9以下)	70	0.3		15%以下	23,764	94.2	
	E70 (7.0~8.9)	1,453	5.8		15~20%	1,447	5.8	
	E90 (9.0~10.9)	8,304	32.6		20~25%	0	0.0	
	E110 (11.0~12.9)	11,356	44.7		25%以上	0	0.0	
	E130 (13.0~14.9)	3,936	15.4		合計	25,211	100.0	
	E150 (15.0以上)	280	1.2					
	合計	25,399	100.0					