







種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50 (6.9以下)	2,451	19.0		15%以下	8,818	73.7	
	E70 (7.0~8.9)	6,137	47.4		15~20%	3,107	25.9	
	E90 (9.0~10.9)	3,563	27.6		20~25%	44	0.4	
	E110 (11.0~12.9)	732	5.6		25%以上	0	0.0	
	E130 (13.0~14.9)	35	0.3		合計	11,969	100.0	
	E150 (15.0以上)	3	0.1					
	合計	12,921	100.0					
杉平角	E50 (6.9以下)	192	19.1		15%以下	755	85.2	
	E70 (7.0~8.9)	527	52.6		15~20%	131	14.8	
	E90 (9.0~10.9)	245	24.5		20~25%	0	0.0	
	E110 (11.0~12.9)	37	3.7		25%以上	0	0.0	
	E130 (13.0~14.9)	1	0.1		合計	886	100.0	
	E150 (15.0以上)	0	0.0					
	合計	1,002	100.0					
桧正角	E50 (6.9以下)	47	0.2		15%以下	27,088	94.9	
	E70 (7.0~8.9)	1,120	3.9		15~20%	1,436	5.1	
	E90 (9.0~10.9)	8,660	30.0		20~25%	0	0.0	
	E110 (11.0~12.9)	13,811	48.0		25%以上	0	0.0	
	E130 (13.0~14.9)	4,766	16.5		合計	28,524	100.0	
	E150 (15.0以上)	398	1.4					
	合計	28,802	100.0					